FLEXcon® Products for Pharmaceutical Labeling

FLX ID	Film and Topcoat	Film Type				Adhesive	Liner	Temperature				Sterilization Method										Peel Adhesion (oz/in)				Security		Printing		Quick-Ship
		Polyester	Polypropylene	Polyethylene	Diacetate			Min Application Temperature F	Min Service Temperature F	Max Service Temperature F	Storage at 70°F - 2 Years, 50% RH	No Sterilization	Autoclave	Ethylene Oxide (ETO)	Gamma	Electron Beam (EB)	No Sterlization	Autoclave	Ethylene Oxide (ETO)	Gamma	Electron Beam (EB)	Stainless Steel	Acrylic	Glass	Polypropylene	Tamper-Evident Film	Fluorescing Adhesive	Conventional	Thermal Transfer	
												Glass Vials (8mm)					HDPE Syringes (16mm)													
210	PHARMcal® PM 150 Clear TC-249	•				V-95	150 Poly	35	-40	302	•	•	•	•	•	•	•	•	•	•	•	50	53	50	4			•		
368	PHARMcal® PM 150 Clear TC-249	•				V-29F	150 Poly	35	-40	302	•						•	•	•	•	•	41	67	47	12		•	•		
212	PHARMcal® PP 200 H Clear TC-332		•			V-232	150 Poly	35	-40	212	•	•	•	•	•	•	•	•	•	•	•	36	44	39	6			•		
211	PHARMcal® PP 200 H Clear TC-332		•			V-232C	150 Poly	35	-40	212	•	•	•	•	•	•	•	•	•	•	•	36	44	39	6		•	•		•
163	Classics Plus® 20085 - DA 200 Clear PTP				•	V-23	50# Kraft	35	-40	212	•	•					•			•	•	55	67	59	10	•		•		•
214	FLEXmark® DA 200 Clear PTP				•	V-88	50# Kraft	35	-40	212	•	•										85	85	85	80	•		•		•
27516	TAMPERmark™ PE 200 White Destruct TC-634			•		V-88	50# Kraft	35	-40	176	•	•	•	•	•	•						Tear	Tear	Tear	Tear	•		•	•	•
443	TAMPERmark™ MM 150 Silver Void TC-249	•				L-156	50# Kraft	35	-40	302	•	•			•	•	•			•	•	Void	Void	Void	Void	•		•		
446	TAMPERmark™ PM 200 White Void II TC-249	•				V-344	50# Kraft	35	-40	302	•						•			•	•	Void	Void	Void	Void	•		•		•
Cryogenic																														
300	CryoFLEX™ PEWM PE 350 F White Matte PTP			•		V-232	50# Kraft	35	-112	176	•	•	•	•	•	•	•	•	•	•	•	64	69	61	21			•	•	•
301	CryoFLEX™ PPC - PP 200 H Clear TC-679		•			V-232	50# Kraft	35	-112	212	•	•	•	•	•	•	•	•	•	•	•	36	44	39	6			•	•	•
302	CryoFLEX™ PPW - PP 230 H White TC-679		•			V-232	50# Kraft	35	-112	212	•	•	•	•	•	•	•	•	•	•	•	41	50	45	6			•	•	•

These products are recommendations only and should be tested in the actual conditions of use.
The typical performance data and recommendations for using FLEXcon products shall be used only as a guide. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose of its intended use.

250-500 MSI minimum order on most products.
* Quick-Ship orders ship within 2 days.
10/11/19

because Sometimes the margin for error is zero.

FLEXcon Industrial Park • Spencer, MA 01562-2642 USA • T 508-885-8296 • F 508-885-8400 • www.FLEXcon.com