## ©2001-2005 Mineral Data Publishing, version 1

**Crystal Data:** Cubic. Point Group:  $4/m \overline{3} 2/m$ . [Massive.]

**Physical Properties:** Cleavage:  $\{001\}$ , perfect; parting on  $\{011\}$  (synthetic). Hardness = 3.5 D(meas.) = n.d. D(calc.) = 3.35

**Optical Properties:** Semitransparent. Color: Colorless. Optical Class: Isotropic. n = 1.837

**Cell Data:** Space Group: Fm3m (synthetic). a = 4.81059(9) Z = 4

**X-ray Powder Pattern:** Synthetic. 2.4059 (100), 1.7009 (54), 2.777 (34), 1.4505 (16), 1.3888 (16), 1.0758 (16), 0.8018 (16)

Chemistry: No analyses of natural material appear to be available.

**Occurrence:** In thermally metamorphosed calcareous ejecta (Vesuvius, Italy); in burning coal measures (Kopeysk, Russia).

**Association:** Calcite (Vesuvius, Italy); fluorellestadite, periclase, magnesioferrite, hematite, srebrodolskite, anhydrite (Kopeysk, Russia).

**Distribution:** On Vesuvius, Campania, Italy. From around Kopeysk, Chelyabinsk coal basin, Southern Ural Mountains, Russia. In the Campbell mine, Bisbee, Cochise Co., Arizona, USA.

Name: From the Old English, quicklime.

**References:** (1) Palache, C., H. Berman, and C. Frondel (1944) Dana's system of mineralogy, (7th edition), v. I, 503. (2) McMurdie, H. (1986) Powder Diff., 1, 266.